

APEX SILT SOCK

APEX SILT SOCKS ARE A DURABLE, POLYPROPYLENE FILTER FABRIC SOCK FILLED WITH 100% RECYCLED WOOD CHIPS THAT ARE USED TO HELP WITH EROSION AND SEDIMENT CONTROL. SILT SOCKS ARE EASIER TO WORK/MANEUVER AROUND ON THE JOBSITE BECAUSE OF THEIR MANAGEABLE WEIGHT AND LOW PROFILE DESIGN

USAGE:

- **SILT FENCE OR STRAW WATTLE AS PERIMETER CONTROL**
- **RAIN SHIELDS/FILTERS**
- **FORM RETENTION/DETENTION AREAS**
- **STORM WATER REDIRECTION/DIVERSION**



- **BUY DIRECT: WE SELL DIRECT AND HAVE COMPETITIVE PRICES AND DISCOUNTS AVAILABLE FOR BULK PURCHASES**
- **SIZES AVAILABLE ARE 8" AND 12" IN SPECIFIED LENGTHS UP TO 150'**
- **DELIVERY AND INSTALLATION AVAILABLE**

Construction	Tubular Knit		
Chemical Reaction	Inert to most soil chemicals including Alkaline, weak acids and salt		
Properties	Fiber Material	Multi-Filament Polypropylene	
	Filament Count	60-120	
	Color	Black	
	Melting Point	166°C	330°F
	UV Protection	Photodegradable/ UV Stabilized	
	UV Resistance	100% at 1000 hr.	
	ASTM G-155		
	Approx. Life Expectancy*	2 – 5 years	
	Specific Gravity	.91 g	
	Roll Properties (Approx.)	Roll Weight	10.9 kg
Roll Length - Relaxed		117 m	360 ft.
Applied Roll Length (Approx.)	12" Diameter	98 m	300 ft.
Strength Properties	ASTM 6241 & ASTM 5035	222 psi	
Packaging	Package Type	Roll	



OUR SOCKS ALLOW WATER TO FILTER THROUGH THEM, SLOWING FLOW AND ALSO CAPTURING SILT AND SEDIMENTS.



APEX SILT SOCKS DO NOT REQUIRE SOIL DISTURBANCE FOR INSTALLATION = REDUCTION OF EROSION AND ALLOWS USAGE ON FROZEN GROUND AND CONCRETE.



OVER 80% OF SEDIMENT AND POLLUTANTS ARE REMOVED AND RETAINED FROM WATER IN RECYCLED WOOD MATERIAL FILLER

Construction	Tubular Knit		
Chemical Reaction	Inert to most soil chemicals including Alkaline, weak acids and salt		
Properties	Fiber Material	Multi-Filament Polypropylene	
	Filament Count	60-120	
	Color	Black	
	Melting Point	166°c	330°F
	UV Protection	Photodegradable/ UV Stabilized	
	UV Resistance ASTM G-155	100% at 1000 hr.	
	Approx. Life Expectancy*	2 - 5 years	
	Specific Gravity	.91 g	
Roll Properties (Approx.)	Roll Weight	10.9 kg	24 lbs.
	Roll Length - Relaxed	117 m	360 ft.
Applied Roll Length (Approx.)	12" Diameter	98 m	300 ft.
Strength Properties	ASTM 6241 & ASTM 5035	222 psi	



Construction	Tubular Knit		
Chemical Reaction	Inert to most soil chemicals including Alkaline, weak acids and salt		
Properties	Fiber Material	Multi-Filament Polypropylene	
	Filament Count	60-120	
	Color	Black	
	Melting Point	166°C	330°F
	UV Protection	Photodegradable/ UV Stabilized	
	UV Resistance ASTM G-155	100% at 1000 hr.	
	Approx. Life Expectancy*	2 - 5 years	
	Specific Gravity	.91 g	
Roll Properties (Approx.)	Roll Weight	10.9 kg	24 lbs.
	Roll Length - Relaxed	117 m	360 ft.
Applied Roll Length (Approx.)	12" Diameter	98 m	300 ft.
Strength Properties	ASTM 6241 & ASTM 5035	222 psi	
Packaging	Package Type	Roll	